

TECHNICAL DATA SHEET

Firwood 36

Alkyd MIO

Description An alkyd intermediate or finish coat for steelwork, containing MIO (micaceous iron oxide) pigmentation.

Finish MIO.

- Features**
- MIO is a non-toxic lamellar pigment which provides excellent barrier protection to moisture permeation. MIO helps improve the corrosion resistance of the paint system.
 - Use as an intermediate or finish coat over a suitable anticorrosive primer.
 - Can withstand dry temperatures up to 95°C.
 - The MIO profiled surface provides excellent adhesion for long term overcoating, providing the surface is clean.

Complies With 2004/42/EC (2012) sub-category A(i) - VOC level below 500 g/l.

Product Code 36- .

Volume Solids 50% ± 2%.

VOC's Below 400 g/l.

Colour Range Dark Grey, Black, Grey/Green, Leaf Green, Green, Brown.

Film Thickness & Coverage	Rec. Min:	Dry	Wet	Theo. Coverage
			40 µm	80 µm
	Rec. Min:	100 µm	200 µm	5.0 m ² /l

Actual coverage varies considerably with factors including surface porosity, roughness, application methods and conditions.

Drying & Overcoating Times at Rec. Min DFT		10°C	20°C	30°C
	Surface Dry:		4 h	2 h
Hard Dry:		36 h	16 h	12 h
Overcoat Min:		48 h	24 h	12 h
Overcoat Max:		Indefinite	Indefinite	Indefinite

Drying and overcoating times can be greatly affected by method and conditions of application such as thickness applied, temperature, ventilation etc. Data above are given as a guide.

TECHNICAL DATA SHEET**Firwood 36****Alkyd MIO**

Surface Preparation	<ul style="list-style-type: none">• All surfaces to be coated should be dry and cleaned as necessary to remove all contamination.• Apply over a suitable primer. Please consult Trimite for advice.
Mixing	Thoroughly stir the coating before use. A power mixer is highly recommended. A wide-bladed stirrer is essential for adequate mixing if only hand stirring. Stir occasionally during use to maintain a homogenous mix.
Mix Ratio	Not applicable – single pack product.
Application Conditions	Throughout the application and the drying/curing time of coatings: (a) good ventilation is required; (b) do not apply when damp weather conditions are likely; (c) the substrate temperature should be at least 3°C above the Dew Point; and (d) the RH (Relative Humidity) should be below 85%. It is advisable not to apply the product when the ambient temperature falls below 5°C. The paint temperature at the time of application should ideally be 15° - 20°C.
Application Details	<ul style="list-style-type: none">• Designed for application by brush or roller as supplied.• May require slight thinning for spray application, please consult Trimite for advice.
Thinner/Cleaner	Firwood 114 Thinner.
SG	1.70 ± 0.15 kg/l.
Flash Point	23° – 60°C.
Shelf Life	Minimum of 2 years from date of manufacture when correctly stored in unopened containers.
Storage	The product should be stored in cool, dry, frost-free conditions, in sealed containers. Most paint materials will apply optimally when at 15° - 20°C.
Health & Safety	Refer to the product's Safety Data Sheet and safety advice on the product label before use.
Date of Issue	Sep 2021.

Information provided in this leaflet is given in good faith but without warranty or assumed liability, as the conditions of application and use are beyond our control. Data are accurate to the best of our knowledge at the time of issue but may be revised in the light of new knowledge and the user should check that data are current before use. The user must satisfy themselves about the product's suitability for their own purpose and refer to the Safety Data Sheet for this product before use. For industrial use only unless specifically stated otherwise.