

Trimite H71

Air Drying Hammer Finish

Description	An air drying, alkyd hammer finish for steelwork and other substrates.
Finish	Hammer.
Features	<ul style="list-style-type: none"> • An attractive and protective finish for metal surfaces, the hammer effect able to disguise metal imperfections. • Hard wearing with good durability. • Can be used as a one coat finish for interior steel surfaces in non-aggressive areas. For exterior exposure and for non-ferrous substrates, a suitable primer is required.
Complies With	Please consult Trimite.
Product Code	-/H71 .
Volume Solids	38% ± 2%.
VOC's	Below 490 g/l.
Colour Range	Limited range, please consult Trimite for details.

Film Thickness & Coverage	Typical:	Dry 30 µm	Wet* 55 µm	Approx. Coverage 6 - 7 m ² /l
--------------------------------------	-----------------	---------------------	----------------------	--

* The above wet film thickness and approximate coverage rate (for conventional spray) will vary with colour and the degree of thinning. Wet film thicknesses are approximate and are based on the typical degree of thinning recommended under 'Application Details'.

Actual coverage varies considerably with factors including surface porosity, roughness, application methods and conditions.

Drying & Overcoating Times at Typical DFT		10°C	20°C	30°C
	Surface Dry:	1 h	30 min	15 min
	Hard Dry:	16 h	8 h	4 h
	Overcoat Min:	nr	nr	nr

May be force dried at temperatures up to 80°C.

nr: not recommended. This product is not usually overcoated, please consult Trimite for advice.

Drying and overcoating times can be greatly affected by method and conditions of application such as thickness applied, temperature, ventilation etc. Data above are given as a guide.

TECHNICAL DATA SHEET**Trimite H71****Air Drying Hammer Finish**

Surface Preparation	<ul style="list-style-type: none">• All surfaces to be coated should be dry and cleaned as necessary.• For optimum results, Trimite H71 should be applied over a suitable primer.• Steel: recommended primers include Trimite GP1 Universal Primer and Trimite SAP2 Etch Primer.• Aluminium and Light Alloys: the recommended primer is Trimite SAP2 Etch Primer.• Wood and MDF: the recommended primer is Trimite GP1 Universal Primer.
Mixing	Thoroughly stir the coating before use. A power mixer is highly recommended. A wide-bladed stirrer is essential for adequate mixing if only hand stirring. Stir occasionally during use to maintain an homogenous mix.
Mix Ratio	Not applicable – single pack product.
Application Conditions	Throughout the application and the drying/curing time of coatings: (a) good ventilation is required; (b) do not apply when damp weather conditions are likely; (c) the substrate temperature should be at least 3°C above the Dew Point; and (d) the RH (Relative Humidity) should be below 85%. It is advisable not to apply the product when the ambient temperature falls below 5°C. The paint temperature at the time of application should ideally be 15° - 20°C.
Application Details	<ul style="list-style-type: none">• Designed for application by brush, conventional or airless spray.• Brush: use as supplied, taking care to finish brush strokes in one direction, to achieve the optimum hammer effect.• Conventional spray: up to 5% ST60 Thinner may be used in the mixed material, to gain a viscosity of 100 - 120 seconds using a BS B4 viscosity cup.• Airless spray: use as supplied, with small additions of ST60 Thinner if required.
Thinner/Cleaner	ST60 Thinner (as thinner) / CT80 Thinner (as cleaner).
SG	0.98 ± 0.15 kg/l.
Flash Point	23° – 60°C.
Shelf Life	Minimum of 1 year from date of receipt when correctly stored in unopened containers.
Storage	The product should be stored in cool, dry, frost-free conditions, in sealed containers. Most paint materials will apply optimally when at 15° - 20°C.
Health & Safety	Refer to the product's Safety Data Sheet and safety advice on the product label before use.
Date of Issue	Feb 2022.

Information provided in this leaflet is given in good faith but without warranty or assumed liability, as the conditions of application and use are beyond our control. Data are accurate to the best of our knowledge at the time of issue but may be revised in the light of new knowledge and the user should check that data are current before use. The user must satisfy themselves about the product's suitability for their own purpose and refer to the Safety Data Sheet for this product before use. For industrial use only unless specifically stated otherwise.