

Trimite SAP2

Two Pack Etch Primer

Description A two pack chromate-free etch primer for non-ferrous metals and steel.

Finish Matt.

- Features**
- Based on a special resin blend including PVB and epoxy.
 - Provides excellent adhesion to steel and non-ferrous metals.
 - Approved for use in a range of DEF STAN systems.

Complies With Please consult Trimite.

Product Code 98/SAP2 .

Volume Solids 15% ± 2%.

VOC's Below 750 ± 20 g/l.

Colour Range Yellow.

Film Thickness & Coverage	Typical:	<u>Dry</u>	<u>Wet*</u>	<u>Approx. Coverage*</u>
			12 µm	45 µm

* The above approximate wet film thickness and coverage rate will vary with the degree of thinning and application technique.

Actual coverage varies considerably with factors including surface porosity, roughness, application methods and conditions.

Drying & Overcoating Times at Typical DFT		<u>10°C</u>	<u>20°C</u>	<u>30°C</u>
		Surface Dry:	nr	10 min
Hard Dry:	nr	2 h	1 h	
Overcoat Min:	nr	2 h	1 h	
Overcoat Max:	nr	16 h	8 h	

nr – not recommended. Low temperatures or high humidity will retard the drying time and could affect the resultant adhesion. Spraying should only be carried out in a warm, dry atmosphere.

Force Drying: can be force dried at temperatures up to 120°C after a flash-off period of 10 min.

Drying and overcoating times can be greatly affected by method and conditions of application such as thickness applied, temperature, ventilation etc. Data above are given as a guide.

TECHNICAL DATA SHEET**Trimite SAP2****Two Pack Etch Primer**

Surface Preparation	<ul style="list-style-type: none">All surfaces to be coated should be dry and cleaned as necessary to remove all rust, mill scale, grease and other contamination. Where necessary, remove weld spatter and grind smooth all sharp metal edges and weld seams.For galvanising and other non-ferrous surfaces, all surfaces should be thoroughly degreased. Any very smooth, shiny areas should be lightly abraded to provide a key.Please consult Trimite for specific project advice.
Mixing	Mix each component separately, and then thoroughly mix together in the mix ratio stated, using a power mixer. Stir occasionally during use to maintain an homogenous mix.
Pot Life at 20°C	12 hours (do not use after this time, even though material may still look fluid).
Mix Ratio	Base (98/SAP2) 1 volume Activator (SAR2) 1 volume.
Application Conditions	Throughout the application and the drying/curing time of coatings: (a) good ventilation is required; (b) do not apply when damp weather conditions are likely; (c) the substrate temperature should be at least 3°C above the Dew Point; and (d) the RH (Relative Humidity) should be below 85%. It is advisable not to apply the product when the ambient temperature falls below 15°C. The paint temperature at the time of application should ideally be 15° - 20°C.
Application Details	<ul style="list-style-type: none">Designed for application by conventional spray.The product is normally used as supplied. Up to 20% Trimite SAT2 Thinner may be used in the mixed material, if required.Low temperatures or high humidity will retard the drying time and could affect the resultant adhesion. Spraying should only be carried out in a warm, dry atmosphere.
Thinner/Cleaner	Trimite SAT2 Thinner (for thinning) / Trimite CT80 (for cleaning).
SG	1.05 ± 0.02 kg/l.
Flash Point	Below 23°C – LOW FLASH MATERIAL.
Shelf Life	Minimum of 1 year from date of receipt when correctly stored in unopened containers.
Storage	The product should be stored in cool, dry, frost-free conditions, in sealed containers. Most paint materials will apply optimally when at 15° - 20°C.
Health & Safety	Refer to the product's Safety Data Sheet and safety advice on the product label before use.
Date of Issue	May 2022.

Information provided in this leaflet is given in good faith but without warranty or assumed liability, as the conditions of application and use are beyond our control. Data are accurate to the best of our knowledge at the time of issue but may be revised in the light of new knowledge and the user should check that data are current before use. The user must satisfy themselves about the product's suitability for their own purpose and refer to the Safety Data Sheet for this product before use. For industrial use only unless specifically stated otherwise.