

TrimaKote HS7

High Solids Primer/Finish

Description	A fast drying alkyd anticorrosive primer/finish for steel and other metals.
Finish	Full Gloss and Semi-Gloss.
Features	<ul style="list-style-type: none"> • Designed for use as an anticorrosive primer/finish for steel containers, modular buildings, machinery and equipment, both for new build and maintenance. • Can be used as a one coat primer/finish or applied over a suitable primer for extended durability. • High solids formulation to minimise solvent use. • Tough, durable finish with excellent water soak resistance. • Excellent Hot Salt Spray Resistance (ASTM B117) anticorrosive performance results – exceeds 600 hours at 100 µm dft.
Complies With	Please consult Trimite.
Product Code	-/HS7- .
Volume Solids	52% ± 2%.
VOC's	Below 420 g/l.
Colour Range	Shade range to order.

Film Thickness & Coverage	Typical DFT:	<u>Dry</u> 75 µm	<u>Wet</u> 144 µm	<u>Theo. Coverage</u> 6.9 m ² /l
--------------------------------------	---------------------	----------------------------	-----------------------------	---

Actual coverage varies considerably with factors including surface porosity, roughness, application methods and conditions.

Drying & Overcoating Times at Min. DFT		<u>10°C</u>	<u>20°C</u>	<u>30°C</u>
	Surface Dry:	2 h	1 h	30 min
	Hard Dry:	4 h	2 h	1 h
	Overcoat Min:	8 h*	4 h*	2 h*
	Overcoat Max:	Indefinite	Indefinite	Indefinite

Force Drying: temperatures up to 80°C for 30 minutes, following a flash-off period of 10 minutes, are suitable.

* This product is not normally overcoated. Minimum overcoating times are therefore given for guidance only - please consult Trimite for detailed advice before overcoating.

Drying and overcoating times can be greatly affected by method and conditions of application such as thickness applied, temperature, ventilation etc. Data above are given as a guide.

TECHNICAL DATA SHEET**TrimaKote HS7****High Solids Primer/Finish**

Surface Preparation	<ul style="list-style-type: none">• All surfaces to be coated should be dry and cleaned as necessary to remove all rust, mill scale, grease and other contamination. Where necessary, remove weld spatter and grind smooth all sharp metal edges and weld seams. Consult Trimite for specific project advice.• Abrasive blast clean to standard Sa2½ (ISO 8501-1:2007), with a surface profile of 50-75 microns.• For areas where abrasive blast cleaning is not possible or not desirable, the surface should be prepared by hand or mechanical means to standard St2 (ISO 8501-1:2007), with care required to avoid 'polishing' the metal surface (producing too smooth a surface for subsequent paint adhesion). Coating lifetime will be significantly reduced if not blast cleaning.
Mixing	Thoroughly stir the coating before use. A power mixer is highly recommended. A wide-bladed stirrer is essential for adequate mixing if only hand stirring. Stir occasionally during use to maintain a homogenous mix.
Mix Ratio	Not applicable – single pack product.
Application Conditions	Throughout the application and the drying/curing time of coatings: (a) good ventilation is required; (b) do not apply when damp weather conditions are likely; (c) the substrate temperature should be at least 3°C above the Dew Point; and (d) the RH (Relative Humidity) should be below 85%. It is advisable not to apply the product when the ambient temperature falls below 5°C. The paint temperature at the time of application should ideally be 15° - 20°C.
Application Details	<ul style="list-style-type: none">• Designed for application by airless spray or air-assisted airless spray. Use a tip size of 15-20 thou and pressure of 2500 – 3000 psi (for air-assisted airless spray) or 3000 – 3300 (for airless spray).
Thinner/Cleaner	Firwood 113 Thinner or YAP 12073 Thinner (for cleaning).
SG	1.27 ± 0.15 kg/l.
Flash Point	23° – 32°C.
Shelf Life	Minimum of 2 years from date of manufacture when correctly stored in unopened containers.
Storage	The product should be stored in cool, dry, frost-free conditions, in sealed containers. Most paint materials will apply optimally when at 15° - 20°C.
Health & Safety	Refer to the product's Safety Data Sheet and safety advice on the product label before use.
Date of Issue	Apr 2023.

Information provided in this leaflet is given in good faith but without warranty or assumed liability, as the conditions of application and use are beyond our control. Data are accurate to the best of our knowledge at the time of issue but may be revised in the light of new knowledge and the user should check that data are current before use. The user must satisfy themselves about the product's suitability for their own purpose and refer to the Safety Data Sheet for this product before use. For industrial use only unless specifically stated otherwise.