

Trimite Plastilac® AF208

Two Pack Polyurethane Paste Pore Filler

Description	A high solids, two pack polyurethane filler for plastic substrates and wood.
Finish	Matt.
Features	<ul style="list-style-type: none"> • Eliminates the problems of unevenness, blowing or poor wetting, in a simple wiping operation. • Designed for use with plastic mouldings and many composites which may have marked porosity or micro voids in the surface, such as GRP, GR Phenolic, polyurethane rigid foam, SMC and fabric reinforced laminates. • An excellent paste filler for wood. • Compatible with a wide range of finishing products.
Complies With	Please consult Trimite.
Product Code	20/AF208.
Volume Solids	45% ± 2%.
VOC's	Below 500 g/l.
Colour Range	Clear.

Film Thickness & Coverage	Typical:	Dry (varies with application)	Wet	Approx. Coverage
	Actual coverage varies considerably with factors including surface porosity, roughness, application methods and conditions.			
Drying & Overcoating Times at Typical DFT		10°C	20°C	30°C
	Surface Dry:	40 min	20 min	10 min
	Hard Dry:	12 h	6 h	3 h
	Overcoat Min:	12 h	6 h	3 h
	Overcoat Max:	14 days	7 days	3 days

Force Drying: increased temperatures may be used to reduce the drying time, after a suitable flash-off period. This procedure must be carried out with care to avoid component deformation. The type of plastic, conditions of moulding and post-mould time will determine the maximum temperature that can be employed.

Drying and overcoating times can be greatly affected by method and conditions of application such as thickness applied, temperature, ventilation etc. Data above are given as a guide.

TECHNICAL DATA SHEET**Trimite Plastilac® AF208**
Two Pack Polyurethane Paste Pore Filler

Surface Preparation	<ul style="list-style-type: none">• Plastic: the substrate must be thoroughly clean and free from mould release agents and static charges. The use of Trimite QT76 Thinner is recommended for cleaning the laminates' surface.• Wood: the substrate must be thoroughly clean, dry and free from foreign matter. Sanding the surface or 'denibbing' is recommended where applicable.
Mixing	Mix each component separately, and then thoroughly mix together in the mix ratio stated, using a power mixer. Stir occasionally during use to maintain an homogenous mix.
Mix Ratio	Base 10 volumes Activator J2511 1 volume.
Pot Life at 20°C	8 hours (do not use after this time, even though material may still look fluid).
Application Conditions	Throughout the application and the drying/curing time of coatings: (a) good ventilation is required; (b) do not apply when damp weather conditions are likely; (c) the substrate temperature should be at least 3°C above the Dew Point; and (d) the RH (Relative Humidity) should be below 85%. It is advisable not to apply the product when the ambient temperature falls below 5°C. The paint temperature at the time of application should ideally be 15° - 20°C.
Application Details	<ul style="list-style-type: none">• Designed for application by wiping.• Wiping: an even coat should be applied to all necessary areas using a cloth. Wiping in different directions is recommended to ensure effective filling. Excess filler should be wiped off to give as smooth a surface as possible, to minimise subsequent flattening.• Impervious gloves should be worn.• Contains isocyanates – the mixed product and the curing agent contain isocyanates (the base does not). Refer to base and curing agent Safety Data Sheets before use.
Thinner/Cleaner	Thinner CT80 (for cleaning).
SG	1.62 ± 0.15 kg/l.
Flash Point	23° - 60°C.
Shelf Life	Minimum of 1 year from date of receipt when correctly stored in unopened containers.
Storage	The product should be stored in cool, dry, frost-free conditions, in sealed containers. Most paint materials will apply optimally when at 15° - 20°C.
Health & Safety	Refer to the product's Safety Data Sheet and safety advice on the product label before use.
Date of Issue	Jan 2023.

Information provided in this leaflet is given in good faith but without warranty or assumed liability, as the conditions of application and use are beyond our control. Data are accurate to the best of our knowledge at the time of issue but may be revised in the light of new knowledge and the user should check that data are current before use. The user must satisfy themselves about the product's suitability for their own purpose and refer to the Safety Data Sheet for this product before use. For industrial use only unless specifically stated otherwise.