

## BONDERITE O-PC 528 BLACK RFU

Known as SUNCORITE 528  
AND 528RFU (READY FOR USE)  
March 2017

### PRODUCT DESCRIPTION

BONDERITE O-PC 528 BLACK RFU provides the following product characteristics:

|                     |                 |
|---------------------|-----------------|
| <b>Technology</b>   | Organic Coating |
| <b>Product Type</b> | Chromium-free   |
| <b>Application</b>  | On Metals       |

BONDERITE O-PC 528 BLACK RFU is a high performance protective coating for metal of any surface profile. During the drying process the metal surface is converted into a phosphate, which in turn is protected by a resin layer containing an anti-corrosive agent. Because of this all in one process it provides a coating with outstanding adhesion and corrosion resistance.

### Application Areas:

BONDERITE O-PC 528 BLACK RFU has outstanding resistance to corrosion (salt spray and humidity) battery acids, fuel oils, solvents and brake fluid.

Because BONDERITE O-PC 528 BLACK RFU can easily be spray applied without complete pretreatment or energy consuming baking processes, it is very popular for the coating of automotive components such as engine mountings, springs, brake components, metal pressings and almost all underbody components.

A single 25 micron thick coating will provide 240 hours ASTM B117 hot salt spray resistance on suitably cleaned mild steel panels, meeting some of the severest automotive specifications in use today.

### TECHNICAL DATA

|  |   |
|--|---|
| Appearance                                     | Semi gloss finish   |
| Viscosity as supplied                          | O-PC 528: 90 ± 5 s<br>BS B4 cup at 25°C<br>O-PC 528 RFU: 35 ± 2 s at 25°C |
| Dry Film thickness                             | 25 microns sprayed reduced 5:1  |
| Flash Point                                    | 21°C  |
| Theoretical Spreading Rate<br>Vol. solids 23.8 | 9.5m <sup>2</sup> /L* Wt. solids 36.8                                     |
| Drying time (sprayed):                         |   |
| Air Dry  | 40 min at 25°C touch dry  |
| Salt Spray ASTMB117                            | 240 h (sprayed test panel)  |
| Hot oil resistance                             | Not affected  |
| Petrol resistance                              | Not affected  |

\* The mileage achieved from this product depends on the efficiency of the application. For example conventional spraying is unlikely to be better than 50% efficient.

### DIRECTIONS FOR USE

#### Preliminary Statement:

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

#### Application:

- Work to be treated with BONDERITE O-PC 528 BLACK RFU should be free of scale, rust, grease or oil. A suitable solvent for grease removal would be Chemiclene 450.
- BONDERITE O-PC 528 BLACK RFU should be stirred prior to use. To coat rough surfaces (castings) BONDERITE O-PC 528 BLACK RFU is used undiluted for a dip application. If sprayed, it should be reduced 5:1 with Reducer 90.
- On smooth surfaces BONDERITE O-PC 528 BLACK RFU is reduced 5:1 with Reducer 90 for both spraying and dipping.
- The coating touch dries at room temperature in 40 min but force drying will accelerate the through hardening. BONDERITE O-PC 528 BLACK RFU needs a minimum application temperature of 18°C to ensure good phosphating.

#### Viscosity when diluted with Reducer 90 (approx.):

|           |                             |
|-----------|-----------------------------|
| Undiluted | approx. 90 s B4 cup at 25°C |
| 20:1      | approx.60 s B4 cup at 25°C  |
| 10:1      | approx.45 s B4 cup at 25°C  |
| 5:1       | approx.30 s B4 cup at 25°C  |

#### Storage:

|  |         |
|--|---------|
| Recommended Storage Temperature, °C                    | 0 to 40 |
| Shelf life, months<br>(in unopened original packaging) | 6       |

A storage life of at least 6 months can be anticipated provided the can remains unopened and stored away from extremes of heat and cold.

Store according to the 'Highly Flammable Liquids and Liquefied Petroleum Gases Regulations 1972'.

#### Classification:

Please refer to the corresponding **Material Safety Data Sheets** for details on:

**Hazards identification**  
**Transport information**  
**Regulatory information**

**ADDITIONAL INFORMATION****Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage:** [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 0.0