

Protection upgraded

SurTec® 495 L

Liquid Desmutting

For Aluminium

Properties

- highly concentrated liquid product
- suited for spray and immersion processes
- easy to handle
- removes even hard etching residues and oxides
- suited for highly alloyed and copper-containing aluminium

Application

	<i>immersion</i>	<i>spray</i>
Make-up value:	17 %vol (10-25 %vol)	10 %vol (5-20 %vol)
Application time:	3 min (2-10 min)	60 s (30-120 s)
Temperature:	23 °C (15-28 °C)	
Agitation:	air agitation	
Spraying pressure:	1 bar (0.5-2 bar)	
Tank material:	steel with acid- and fluoride-resistant internal coating	
Heating:	not required	
Exhaust:	recommended for worker's protection	
Hint:	A slight turbidity of the bath solution does not disturb the desmutting process.	

Recommended process sequence (for aluminium parts):

1. Immersion cleaning SurTec 133
2. Alkaline etching SurTec 181
3. **Desmutting SurTec 495 L**
4. Passivation SurTec 650
5. Rinse with deionised water (max. 30 µS/cm)
6. Hot air drying at max. 65 °C

Between each step, there has to be rinsed. The rinsing methods need to be adapted to the plating line.

Technical Specification

(at 20 °C)	Appearance	Density (g/ml)	pH-value (conc.)
SurTec 495 L	liquid, yellow-brown, clear	1.367 (1.35-1.39)	< 1



Maintenance and Analysis

Analyse and adjust the concentration of SurTec 495 L regularly.

Sample Preparation

Take a bath sample at a homogeneously mixed position and let it cool down to room temperature, if necessary. If the sample is turbid, let the turbidity settle down and decant or filter the solution through a fluted filter.

SurTec 495 L - Analysis by Titration

Reagents: 0.1 mol/l EDTA solution (EDTA-di-Na salt, Titriplex III)
caustic soda solution (10 %)
indicator: 5-sulfo salicylic acid · 2 H₂O (2 % solution)

Procedure:

1. Pipette 5 ml bath sample into a 250 ml Erlenmeyer flask.
2. Dilute to approx. 100 ml with deionised water.
3. Adjust the pH-value to pH 2.5 with 10 % caustic soda solution.
4. Add 2 ml indicator solution.
5. Titrate with 0.1 mol/l EDTA solution from deep red to light yellow until no further brightening is observable (*there is no sharp colour changing point*). If the colour returns to red again, add more EDTA solution, until the yellow colour remains stable for at least 5 minutes.

Calculation: consumption of EDTA solution in ml · 1.84 = %vol SurTec 495 L

Bath Contamination

Aluminium content: max. 5 g/l
Copper content: max. 0.5 g/l

Ingredients

- sulfuric acid
- fluorides
- nitrates

Consumption and Stock Keeping

The consumption depends heavily on the drag-out. To determine the exact amounts of drag-out, see **SurTec Technical Letter 11**.

The following value can be taken as estimated average consumption:

SurTec 495 L 40 ml per m² of treated surface

In order to prevent delays in the production process, per 1000 l bath the following amount should be kept in stock:

SurTec 495 L 200 kg

Product Safety and Ecology

European legislation). The safety instructions and the instructions for environmental protection have to be followed in order to avoid hazards for people and environment. Please pay attention to the explicit details in our Material Safety Data Sheets.

Warranty

We are responsible for our products in the context of the valid legal regulations. The warranty exclusively accesses for the delivered state of a product. Warranties and claims for damages after further processing of our products do not exist. For details, please find our country-specific **General Terms and Conditions** for downloading on our homepage or ask your regional SurTec representative.

Further Information and Contact

If you have any questions concerning the process, please contact your local technical department.

For further information and contact details, please visit our homepage:

<http://www.SurTec.com>

15 January 2020